



TKB Trading
 939 E 11th St
 Oakland, CA 94606
 www.tkbtrading.com
 support@tkbtrading.com

SOFT VIOLET

COA-Representative Analysis

DESCRIPTION	Violet pigment of Bismuth Oxychloride coated mica
Shelf Life	5 years

Typical Composition	By Weight	CAS No.	Color Index	INCI Name	EINECS
BiOCl	35–45%	7787-59-9		Bismuth Oxychloride	232-122-7
Mica	30–40%	12001-26-2		Mica	310-127-6
Manganese Violet	15–25%	10101-66-3	77742	Manganese Violet	233-257-4
Magnesium Stearate	0.5–5%	557-04-0		Magnesium Stearate	209-150-3

METHOD: CC-PT-24	SPECS	
Pigment Color	$\Delta E \leq 2.7$	
Loss on drying	2% max.	
As	1 ppm max.	
Pb	5 ppm max.	
Hg	1 ppm max.	
Particle size (D ₅₀)	13 – 18 μm	
Bulk density	0.2 – 0.4	
pH	6 – 8	
Microbiological	Bacteria: ≤ 10 CFU/g	
	Yeast: ≤ 10 CFU/g	
	Mold: ≤ 10 CFU/g	

The information contained herein is based on current knowledge and experience and from tests performed by an outside entity. No responsibility is accepted that the information is sufficient, complete, or correct in all cases. Users should consider the data only as a supplement to other information. Product analysis should be verified by Users prior to usage. Users should make independent determination of suitability and completeness of information from all sources to assure proper use of this product and the safety of User's customers. Users should be aware that results may vary depending on use of and/or mixture of this product with other products. The determination of suitability of the above product for any particular use is solely the responsibility of the User.